

**LOCTITE® FREKOTE FRP-NC**

Known as  
**Frekote® FRP-NC**  
September 2015

**Description**

Loctite® Frekote® FRP-NC is a unique release interface specifically formulated for reinforced polyester gel coats (and other associated resin systems). This semi-permanent release coating chemically bonds to the mold surface, forming a micro thin release film. Loctite® Frekote® FRP-NC provides a high gloss finish and minimal mold build-up thus eliminating buffing and cleaning between applications. Multiple releases per application also contributes to major time savings.

**Features**

Minimal mold build-up  
Multiple releases per application  
High gloss finish  
Maximum mold utilization  
Lower mold maintenance costs  
Fast cure

**Properties**

Appearance	Clear liquid
Odor	Hydrocarbon
Solvents	Aliphatic Hydrocarbon, Dibutyl Ether
Specific Gravity	0.770 +/- 0.010
Flash Point	28°C (82°F) Tag Closed Cup.
Shelf Life	One year from date of manufacture
Special Cautions	Moisture sensitive, keep container tightly closed when not in use.
Application Temp	13°C - 40°C (55°F - 105°F)
Thermal Stability	400°C (750°F)

**Mold Preparation**

To work effectively, Frekote Release products must be applied to thoroughly cleaned and dried mold surfaces. All traces of waxes, sealers, rubbing compounds or other release agents must be completely removed. Remove any contaminants with Frekote PMC, PMC Plus or suitable cleaning solvent. Light industrial abrasives can be used to remove heavy resin build-up.

**Mold Sealing**

New Molds: Full curing of new molds is advisable to ensure the best bonding of the Frekote to the mold surface. New fiberglass and epoxy molds should be cured per manufacturer's instructions before starting full-scale production.

Green molds and recently repaired areas must be sealed with Frekote FMS prior to using Frekote releasing interfaces. Porous and damaged mold surfaces should also be sealed with FMS. Consult FMS Technical Data Sheet for specific application instructions.

**Application \*Consult MSDS Prior To Use.\***

1. Apply with a clean lint free 100% cotton cloth. Soak cloth with Loctite® Frekote® FRP-NC until it is wet, but not dripping.
2. Wipe a smooth, wet film over a 2' x 2' to 2' x 3' area of the mold surface. Do not over apply.
3. Wait 10-20 seconds at 21°C (70°F) after application. Gently wipe dry with, a second clean dry, cotton cloth.

**NOTE:** Changes in temperature will affect solvent dry time. At temperatures below 18°C (65°F), waiting time between wiping on and drying off will be longer than 20 seconds. A general guideline is to wait until the edges of the wiped area begin to creep inwards indicating that evaporation has progressed sufficiently. Light hand pressure is all that is needed. No hard rubbing is required. Change cloth frequently to ensure proper drying of the mold.

4. Coat entire mold surface in this manner slightly overlapping the last area coated. Apply a maximum of 6 coats initially. A couple of extra coats can be applied in high wear areas for added slip. Allow 15-20 minutes cure time at room temperature between coats and after the final coat.
5. Commence molding. A single coat of Loctite® Frekote® FRP-NC should be applied after each release for the first two to three releases. This helps to condition the mold, which in turn offers multiple releases on future production.

**Mold Touch up**

Abrasion will gradually cause wear and parts will begin to adhere to the mold surface if a continuous release film is not maintained. If release becomes difficult, simply touch-up the area affected. Only one coat is usually required for touch-up. Use either Loctite® Frekote® FRP-RS or Loctite® Frekote® FRP-NC for touch-ups.

**Flammability/Storage**

Loctite® Frekote® FRP-NC contains flammable solvents. The product should always be used in well-ventilated areas. Store in a cool, dry place. Consult MSDS for complete details.

**Note**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results.

We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.