

CRYSTIC 1087PAELV

Low exotherm versatil spray resin

Introduction

CRYSTIC 1087PAELV is an hybrid DCPD / orthophtalic pre-accelerated, low styrene emission and thixotropic unsaturated polyester resin. It contains a colour change system and will change from blue to natural colour when the catalyist is added to the resin.

Application

CRYSTIC 1087PAELV is designed mainly for spray application but is also suitable for contact moulding. CRYSTIC 1087PAELV is a versatil resin and may be used for most general purpose mouldings.

Features and Benefits

<i>Features</i>	<i>Benefits</i>
Low viscosity.....	Easy impregnation of the reinforcement
Rapid hardening.....	Fast mould turn – round
General purpose.....	Only one resin for many applications
Colour change system.....	Secures that catalyist is well added and mixed
Low styrene emission.....	Better healthcare for the workers, lower smell for the neighbourhood

Formulation

The following cold curing formulation is recommended:

CRYSTIC 1087PAELV:	100 parts
Catalyist M :	1 to 2 parts

Catalyist M is a Methyl Ethyl Ketone Peroxyde at 50% such as the Butanox M50 from AKZO.

Variants

CRYSTIC 1087MPAELV is the summer version with a longer geltime.

Gel time

The ambient temperature, the amount and type of catalyst control gel time of resin formulations. Curing should not be carried out at a temperature below 15°C.

The resin must be allowed to attain the workshop temperature before being used.

Parts of Cat. M for 100 parts of 1087PAELV	1	2
Gel time at 15°C (min)	68	35
Gel time at 20°C (min)	47	28
Gel time at 25°C (min)	31	18

Additives

Since certain pigments, fillers or extra styrene may affect properties of **CRYSTIC 1087PAELV** their effect should be evaluated before addition to the formulation.

Post-Curing

For most applications satisfactory result will be obtained by curing at room temperature (20°C). Some improvement in properties may be obtained by post-curing 16 hours at 40°C after release from the mould

Typical Properties

On liquid resin :

Viscosity at 25°C (Rhéomat 37,35 sec ⁻¹)	dPas	2.5 – 3.5
Specific gravity		1.10
Volatile content	%	38 - 41
Aspect		Blue thixo
Stability in dark at 20°C	Months	3
Gel time at 25°C with 100 parts of Resin and 2 parts Catalyst M 1087MPAELV	min	16 – 21 27 - 32

On fully cured resin:

Barcol Hardness (Model GYZJ 934-1)		*** 39
Elongation at break	%	1.8
Heat Deflection Temperature (1.80 MPa)	°C	75
Specific gravity		1.2
Tensile strength	MPa	53
Tensile modulus	MPa	3200
Volume shrinkage	%	8.3

BS 2782 : 1980

1Mpa = 1MN/m² approx. 10.2 kgf/cm²

*** 24h at 20°C then post cured 3h at 80°C, except for HDT : 24h at 20°C, then 5h at 80°C, then 3h at 120°C

Packaging

CRYSTIC 1087PAELV is supplied in 225 kg or 1100 kg containers. Bulk supplies can be delivered by road tanker.

Health and Security

The most important protective measures to be taken with unsaturated resins and resin systems are:

- Correct storage
- Stock rotation
- Adequate workplace ventilation
- Local extraction where vapour
- Concentrations may build up or are high
- Use of fresh air masks in confined spaces or spray applications outside of spray booths
- Work place monitoring of vapour concentrations
- Good housekeeping
- Systematic work routines
- Competent personnel
- Supervision, training and instruction
- Fire precautions
- Correct disposals

Points of Caution

Monomer and solvent vapour concentrations above certain levels can be hazardous to health and safety. The safety risks are associated essentially with the fire and possible explosions. The risks to health come mainly from the build up of vapours in the workplace in excess of certain limits and the limits applicable to the user's country should be determined.

The symptoms of the more common vapours are similar, i.e. dry irritating throat, coughing, drowsiness, and headache. Both liquids and vapours may cause skin irritation and dermatitis to susceptible personnel.

All information is given in good faith but without warranty. We cannot accept responsibility or liability for any damage, loss or patent infringement resulting from the use of this information.

UK-UP-1087PAELV
Mars 2006

