

CRYSTIC[®] RTR 4010PA

RAPID TOOLING RESIN

Introduction

Crystic RTR 4010PA is a new, improved rapid tooling resin which incorporates better handling properties, lower viscosity, improved shrinkage control and is catalysed with standard MEKP catalyst. RTR 4010PA is a thixotropic, filled, low profile resin for hand-lay mould making applications.

RTR 4010PA helps to achieve faster mould making and eliminates surface distortion, forming part of Scott Bader's new mould making system, which also comprises of Crystic GC15PA and Crystic VE679PA skincoat.

Applications

Crystic RTR 4010PA is designed for hand-lay applications and must be allowed to attain a minimum workshop temperature of 18°C before use (20°C to 24°C is recommended). It should be mixed thoroughly prior to use and requires only the addition of MEKP catalyst to start the curing reaction. The recommended catalyst is Catalyst M (or Butanox[®] M50), which should be added at 1% into the resin and thoroughly dispersed. The recommended resin-to-glass ratio for chopped strand mat glass reinforcement is at least 2.5-to-1 by weight.

The design, complexity and size of the mould will determine optimum reinforcement levels and thickness. At least 3 layers of 450gsm chopped strand glass mat, or equivalent, is required and should be applied in a single operation to achieve sufficient cure and low shrink performance. The material will undergo a colour change becoming whiter as the curing reaction takes place.

Typical Properties

The following tables give typical properties of Crystic RTR 4010PA:

Properties	Unit	Liquid Resin
Appearance		Cream / Opaque
Viscosity at 25°C (ICI Cone and Plate)	Poise	5 - 6
Specific Gravity at 25°C		1.35
Volatile Content	%	25 – 30%
Geltime at 25°C with 1% Catalyst M **	Minutes	25-34
Stability (at less than 20°C in original container)	Months	3
Mechanical Properties		Laminate Properties
HDT***	°C	63
Tensile Strength*	MPa	114
Tensile Modulus*	MPa	8075
Elongation at Break*	%	2.0

* Glass content 28%, laminate made with 3 layers of 450gsm CSM; 16hrs at 40°C post cure

** Catalyst Butanox M50 can be used

*** Property of the cast resin; 16hrs at 40°C post cure

Post Curing

Satisfactory laminates for many applications can be made from Crystic RTR 4010PA by curing at workshop temperature (20°C). However, for optimum properties and long term performance, moulds made with RTR 4010PA should be post cured before being put into service. The laminate should be allowed to cure for 24 hours at 20°C and then oven cured for 16 hours at 40°C.

Additives

Crystic RTR 4010PA is supplied ready to use and already has pigment added. No further pigments or other materials should be added as this could adversely affect the degree of cure and mechanical properties of the cured resin.

Storage

Crystic RTR 4010PA should be stored internally in its original container. It is recommended that the storage temperature should be between 15 – 20°C. Ideally, containers should be opened only immediately prior to use.

Packaging

Crystic RTR 4010PA is supplied in 25kg and 225kg containers.

Health and Safety

See separate Material Safety Data Sheet.

Version: November 2016

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com