



SELCOM SRL via della Torre n. 17 31010 FREGONA (TV) ITALY phone +39 0438 585166

phone +39 0438 585166 modem fax +39 0438 585172 manual fax +39 0438 916049 cap. soc. EURO 101490,00 cod. fisc. e p.i. IT 02369430265 trib. Treviso n. 33642 reg. soc. c.c.i.a.a. Treviso n. 206094 M. estero TV 028944 E-mail: info@selcom-srl.com

MULTIAXIAL TECHNOLOGY (NCF) unidirectional & stitched multiaxial fabrics in glass, carbon, aramid... and hybrids for the composite industry

internet: www.selcom-srl.com

Technical Data Sheet

PRODUCT NAME EBX600 Biaxial fabric ±45° in "E" glass

layers	angle tolerance	fiber	plan	tex	areal weight gr/m²	areal weight tolerance
Oº	-	Polyester yarn	L6	8,0	8	± 3 %
+45º	± 1º	E glass : NEG Roving 2002 or equivalent	L6	300	306	± 3 %
-45º	± 1º	E glass : NEG Roving 2002 or equivalent	L6	300	306	± 3 %
		TOTAL gr/m²	-	-	620	± 3 %

Characteristics for fabric

Characteristics for raphic	
lunghezza rotolo - standard roll length:	mtl 50 ± 1 mtl
larghezza rotolo - standard roll width:	mm 1270 ± 20 mm
peso netto rotolo - net roll weight:	Kg. 39,4 ± 3 %
tolleranza sulla grammatura – areal weight tolerance:	$\pm 3\% (\pm 19 \mathrm{gr/m^2})$
grammatura teorica – theoretical areal weight:	gr/m² 620
identificazione rotolo - ident roll:	EBX600
tipo di legatura - knitting type:	pillar
filo di legatura – stitch yarn:	polyester, texturated, 8,0 tex

Characteristics for filament yarn

Characteries of marriers yarr						
tipo fibra – type:	NEG Roving 2002					
binder content:	0.55 – 0.65 % (nominal)					
produttore – manufacturer:	Nippon Electric Glass fiber					
densità volumetrica – volumetric density:	gr/cm³ 2.59 – 2.62					
diamentro filamento – filament diameter:	µm 14 (300 tex)					
resistenza a trazione – tensile strength:	Mpa 1900 – 2400 (ASTM D-2343) *					
modulo a trazione – tensile modulus:	Gpa 69 – 76 (ASTM D-2343) *					
allungamento a rottura – elongation at break:	3.5 - 4 %					

^{*}According to ASTM D-2343. All these informations can be used for material selection purposes only.

NB: THIS DOCUMENT IS COMPUTER GENERATED AND IT'S VALID WITHOUT SIGNATURE Fregona Iì 02/03/2021

Technical Manager Ing. Giovanni Fardin



DNV-GL TYPE APPROVED PRODUCT - Cert. No. TAKOOOO17V



SELCOM Srl is a weaver of technical textiles from continuous filaments (rovings). All information supplied by or on behalf of SELCOM Srl in relation to its products, whether in the nature of data, recommendations or otherwise, has been given in good faith and in compliance with technical and commercial information supplied by raw materials (fibre) manufacturers. All information aforementioned are supported by its own experience and believed reliable but SELCOM Srl declines all responsibility in respect of the application, processing ore use of the aforementioned information or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify or any consequence thereof. SELCOM Srl believes that it is the user that shall determine the suitability of a product for its end-use and the user that assures all liability in connection therewith.

M10-1-02.DOC Ed.01-Rev.00-12.05.10